

# Technical Data Sheet

Transtar eSelect Universal Clearcoat is a two component, universal urethane clearcoat designed for spot, panel, and overall refinishing. It is fast drying, easy to use, and provides a durable finish and gloss.

## SUITABLE SUBSTRATES

Substrate		Substrate		Substrate	
Solvent-borne Basecoat	✓	Waterborne Basecoat	✓	Acrylic Lacquer	
1K Enamel		2K Enamel	✓		
OEM Finish & Old Paint Work - Reversible		OEM Finish & Old Paint Work - Non-Reversible	✓		

## MIXING



By Volume: 4 parts OR3301 eSelect Universal Clearcoat  
 1 part OR1214/OR1224/OR1234 Activator  
 Optional: Up to 5% 6700 or 6700-F Series Urethane Grade Reducer\*

Pot Life 3 hours (@70°F (21°C) and 50% relative humidity)

\* Use reducer according to shop conditions. Using reducers other than Zero VOC Urethane Grade Reducers will increase VOC.

## FLASH TIMES/DRY TIMES



Flash Between Coats 5-25 minutes  
 Dust Free 10-25 minutes  
 Dry to Sand 8-10 hours  
 Delivery 12+ hours MIN  
 Force Drying 30 minutes @ 140°F (25°C) after 5-10 minute flash

Activator	Flash Time	Dust Free
OR1214 Fast	5-10 min	10-15 min
OR1224 Medium	10-15 min	15-20 min
OR1234 Slow	20-25 min	20-25 min

## SURFACE PREPARATION



Tack surface thoroughly before application.

## SPRAY GUN SET-UP/APPLICATION



Gun Type HVLP/LVLP Gravity Feed  
 Fluid Tip 1.2 - 1.6 1.2 - 1.6  
 Air Pressure 10 PSI @ aircap 35 - 50 PSI @ gun inlet  
 Mil Thickness: 2-3 coats (@ 1.2 mils per coat dry film thickness). Must have a minimum of 2.2 mils.

## LIMITATIONS & PRECAUTIONS

- For use only by professional, trained painters. Not for sale to or use by the general public.
- Before use, read and follow all TDS, label and SDS precautions.
- See next page for more detailed production application.

# Technical Data Sheet

## SPRAY GUN SET-UP

Gun Type	Siphon Feed	Gravity Feed	Pressure Feed	HVLP/LVLP
Fluid Tip	1.2-1.6 mm	1.2-1.6 mm	1.0-1.2 mm	1.2-1.4 mm
Air Pressure	35-50 PSI (@gun)	35-50 PSI (@ gun)	40-50 PSI (@ gun)	10 PSI (@ aircap)
Fluid Pressure	N/A	N/A	8-10 PSI	N/A

*Always refer to gun manufacturer's recommendation for proper set up and spray pressure.*

## SURFACE PREPARATION

Tack thoroughly before application.  
For blending clearcoat refer to SOP #513 and # 514.

## ADDITIVES

**Additives:** Kicker (6417) - Should not be used in temps above 65°F (24°C). For temps below 65°F (24°C) use ½ oz per sprayable quart.  
Appearance Improver (6487) - Can be used at a rate of 1-2 oz per sprayable quart.  
Fisheye Remover (6737) - Can be used at a rate of ½ oz per sprayable quart.  
Universal Urethane Flex Additive (9194) - Use with soft, flexible substrates. Refer to 9194 TDS for mixing information.

## APPLICATION & FILM BUILD

Apply 2 - 3 flowing coats (2.2 - 3.6 mils @ 1.2 mils per coat) using the spray gun setting listed above. Flash for 5 – 25 minutes depending on activator used. Keep spray gun nozzle 6 - 10 inches from the vehicle to avoid entrapment of air in paint film. Always keep containers tightly closed to prevent moisture contamination. Clean equipment thoroughly after use.

**Critical Recoat Time:** Do not flash for more than 1 hour between coats. If more than 1 hour @ 70°F (21°C) is reached, wait at least 5 hours and scuff with a red or gray scuff pad before applying more clear or basecoat. Lightly scuff surface and degrease before application.

**Film Build:** 2-3 coats @ 1.2 mils. Must have a minimum of 2.2 mils and not to exceed 3.6 mils.

## PRODUCT SPECIFICATIONS

Weight per gallon: 7.62	Shelf Life: 3 years
RTS Solids by Weight: 36%	Color: Clear Liquid
Approximate Coverage: 474 ft <sup>2</sup> /gal @ 1 mil	Size: Gallon (OR3301), Quart (OR1214, OR1224, OR1234)

## REGULATORY

Category: Clearcoat	OR3301	OR1214	OR1224	OR1234
VOC Actual	3.66#/gal (439 g/l)	3.4#/gal (407 g/l)	3.52#/gal (422 g/l)	3.5#/gal (419 g/l)
VOC Regulatory	4.76#/gal (571 g/l)	3.72#/gal (446 g/l)	3.63#/gal (435 g/l)	3.65#/gal (438 g/l)
Weight % of Volatiles	68.13	49.93	46.2	46.20
Weight % of Water	0	0	0	0
Weight % of Exempt Compounds	20.06	11.00	4.00	5.50
Volume % of Exempt Compounds	23.12	8.62	3.00	4.25
Density of Material #/gal	7.62	8.73	8.34	8.59
		with OR1214	with OR1224	with OR1234
Ready to Use (less water, less exempt compounds)		4.53#/gal (542 g/l)	4.49#/gal (538 g/l)	4.5#/gal (539 g/l)